



HERITAGE MASONRY REPAIR MORTAR CCS60 – CONCRETE AND CAST STONE

Product Data Sheet

Description and Use

CCS60 is an engineered repair mortar designed specifically to match the characteristics of concrete and cast stone that facilitates fast, easy and extremely durable repairs with excellent visual match. Mineral-based, single component and cementitious, CCS60 is mixed only with water. No synthetic polymer additives are added. Formulated using only natural mineral binders, CCS60 exhibits excellent UV, freeze-thaw and salt resistance while maintaining flexibility and vapor permeability.

CCS60 concrete and cast stone repair mortar is typically installed in-situ to replace missing, damaged or deteriorated surface areas on concrete and cast stone. Repairs can be built out on vertical concrete and cast stone surfaces, without forms, up to 3 inches in a single lift. It is also possible, using CCS60, to cast projections and entire replacement masonry units. CCS60 is simply mixed with water then applied and finished by hand, typically within a few hours. Utilizing CCS60 on concrete and cast stone restoration projects results in substantial cost savings initially due to speed of installation and later due to durability of repairs. Skilled restoration masons can easily apply CCS60; training is offered but no special certification is required.

Features and Benefits

- Sympathetic product formulation ensures compatibility with masonry substrates based on key performance measures, resulting in superb long-term repair durability
- CCS60 can be typically be specified and installed as a direct substitute to other mineral-based masonry repair mortars
- Custom-matched colors and aggregate profiles produce unbelievable visual accuracy
- USHG provides unmatched product and project support, for one pail or hundreds, to ensure excellent results for every installation.

Sales Product and Project Support

US Heritage Group supports, sells and ships all products directly to ensure we consistently deliver the highest quality results possible. Contact USHG for a variety of support services:

- Specifier education
- Project-specific technical advice
- Specification guides and support
- Custom color and aggregate matching
- Installation guides and training

Technical Data

Compressive Strength: (ASTM-109)	3 days	2,900 psi
	7 days	4,360 psi
	28 days	5,800 psi
Bond Strength: (ASTM C-882)	1,680 psi	
Flexural Strength: (ASTM C-348)	1,755 psi	
Modulus of Elasticity: (ASTM C-469)	2,670 psi	
Porosity:	10%	
Absorption:	8 to 10%	
Linear Coefficient of Thermal Expansion:	4.5 to 5.0 x 10 ⁻⁶ /°F	

Packaging and Coverage

1-quart plastic jar (2 lbs.)	35 cubic inches of mixed material
1-gallon plastic pails (9 lbs.)	150 cubic inches of mixed material or 1 square foot at 1" thickness
5-gallon plastic pails (44 lbs.)	0.4 cubic feet or 4.8 square feet at 1" thickness

Limited Warranty

U.S. Heritage Group, Inc. warrants this product to be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is LIMITED to the replacement of the product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given in writing to U.S. Heritage Group, Inc., 2900 North Kearsarge Ave., Chicago, IL 60641. THIS LIMITED WARRANTY IS ISSUED AND ACCEPTED IN LIEU OF ALL OTHER EXPRESSED WARRANTIES AND EXPRESSLY EXCLUDES LIABILITY FOR CONSEQUENTIAL DAMAGES.

US Heritage Group

2900 North Kearsarge Ave, Chicago IL 60641

P: 773.286.2100 F: 773.286.1852 E: info@usheritage.com

www.usheritage.com



HERITAGE MASONRY REPAIR MORTAR CCS60 – CONCRETE AND CAST STONE

Product Data Sheet

Surface Preparation

Repair area should not be less than 1/4" in depth when using CCS60. For patches less than 1/4" in depth or with feathered edge, use Dispersed Hydrated Lime Spachtel. Do not apply material to areas with feathered edges.

1. Square cut edges of repair area using hand tools or pneumatic carving tools.
2. Sound off and chisel out all loose and deteriorated stone.
3. Clean the area with clean water and a stiff-bristled brush to remove any loose stone particles.
4. Neutralize any salt deposits (efflorescence and subflorescence) with distilled water.
5. Dampen with clean water until glistening with no standing water.

Mixing

Wear safety goggles, latex gloves and a dust mask equipped with P-2 filters or equivalent for protection. Dry material should be rebleded prior to mixing with water to evenly distribute any particles that may have settled in transit. The consistency of the mixture should be similar to that of wet sand (not mud). Do not over mix.

Temperature and humidity will affect the amount of water required.

1. Add 5 parts dry powder to approximately 1-part potable water in plastic pail.
2. Mix thoroughly by hand or by low-speed drill (250 to 500 rpm) for 1-2 minutes or until no dry material remains.
3. Check consistency by hand squeezing then breaking a ball of mixed material.
4. If necessary, add fractional part powder or water to adjust and re-mix in 30 second increments for a maximum of 2 minutes.

Application

All repairs require a minimum two-coat application consisting of a slurry coat and a build-out coat. Additional build-out coats may be applied to meet the required thickness. Material can be applied up to 60 minutes after mixing with water, depending on temperature, relative humidity and type of finish specified. Do not install material below 40°F or above 90°F.

Slurry Coat

1. In a separate container gradually add water to a small amount of mixed material until it reaches a soupy consistency.
2. Apply as thin slurry coat to the surface that will be built out. The skim coat can be applied with a brush or with a hand to coat completely.
3. Start build-out on wet slurry. Reapply slurry to any dry areas prior to build-out coat application

Build-Out Coats

Build-out coats should be applied with small trowel or by hand. Multiple build out coats (lifts) should be used if the total build out depth is over 3".

1. Apply the first build out coat over a wet slurry coat.
2. For any additional build-out coats add small fraction of powder to tighten mix.
3. The surface "skin" of build-out coats should be removed when thumbprint hard before applying the next lift of material wet-on-wet.
4. Apply final build-out coat minimum 1/4" beyond desired edge

Cleaning

1. Clean all tools and surfaces with clean water immediately after application before the mortar has time to dry.
2. Remove surface smears/residue by repeated application of clean water and brushing until all material is removed. Avoid contact of water or brush with repair area.
3. Remove hardened material mechanically.

Finishing and Curing

CCS60 is ready to finish when thumbprint hard. Material can be hand tooled up to 3 hours after mixing. When material becomes too hard to finish by hand it can be finished with stone carving tools. Always tool away from edges, corners, projections, and towards stone.

1. To hand-tool flat surfaces, draw a straight edged stainless-steel tool across the finish surface. Use the tool at an angle, as the tool can create a surface smoother than the existing stone if it is drawn flat against the material.
2. To hand-tool shapes in the material, use an angled stainless-steel tool to scrape away material into the desired design.
3. Tool entire surface to remove remaining "skin".
4. Protect finished repair from weather and direct sunlight by keeping it covered with plastic or burlap for 24 hours before exposing it to temperatures below 40°F or above 90°F.
5. For best visual match lightly mist repair area with clean water several times a day, for first 3 days after installation.

Storage

US Heritage Group CCS60 has a shelf life of 1 year when stored at a constant temperature and relative humidity in its original sealed container.

US Heritage Group

2900 North Kearsarge Ave, Chicago IL 60641

P: 773.286.2100 F: 773.286.1852 E: info@usheritage.com

www.usheritage.com